

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 1 / 22

Applicant : Mid Ocean Brands B.V.
Address : Unit 711-716, 7/F., Tower A, 83 King Lam Street, Cheung ShaWan,
Kowloon, Hong Kong.

Below information was/were submitted and identified by the applicant:

Product Name : Sport bag
Model : MO2987
Main material : PU, Polyester
Manufacturer info. : /
Supplier info. : 119706
Buyer info. : /
Country of Destination : /
Country of Origin : /

Sample Received : Sep. 8, 2026
Test Period : Sep. 8, 2026 - Oct. 21, 2026
Test Requested : Refer to next pages
Test Method(s) : Refer to next pages
Test Result(s) : Refer to next pages

Tested By: Lyra Jin
Lyra Jin

Reviewed By: Ally Lu
Ally Lu

Approved By: David Chen
David Chen
Lab Director



TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 2 / 22

RESULT SUMMARY

As requested by the client, test item(s) as below:

Test Item(s)	Conclusion
1. Lead (Pb) content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 63)	PASS
2. Cadmium (Cd) content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 23)	PASS
3. AZO content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 43)	PASS
4. Color Fastness to Rubbing-Client's Requirement	PASS
5. PAHs content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 72)	PASS
6. Phthalates content-Regulation (EC) No.1907/2006, REACH Annex XVII (entry 51&52)	PASS

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 3 / 22

TEST PART DESCRIPTION

- 1# Black synthetic leather with fabric backing main body
- 2# Black woven core (inside handle)
- 3# Black lining
- 4# Black binding
- 5# Black plastic strip (internal rib)
- 6# Silver metal ring (hanging ring)
- 7# Silver metal rivet
- 8# Black plastic base board
- 9# Black plastic foot pad
- 10# Black plastic zipper teeth
- 11# Black zipper fabric
- 12# Black metal zipper slider
- 13# Silver metal screw
- 14# Beige synthetic leather with fabric backing main body
- 15# Navy blue synthetic leather with fabric backing main body
- 16# Silver metal zipper slider
- 17# White synthetic leather with fabric backing main body
- 18# Black plastic gasket
- 19# Blue zipper fabric
- 20# Blue plastic zipper teeth
- 21# Beige zipper fabric
- 22# Beige plastic zipper teeth
- 23# White zipper fabric
- 24# White plastic zipper teeth
- 25# White foam

TEST RESULT(S)

1. Lead (Pb) Content

Test Method: With reference to EPA 3052-1996 & EPA 6010D-2018, analysis was performed by ICP-OES.

Test Item	Unit	MDL	Test Result(s)				Limit
			1#	2#	3#	4#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	N.D.	500

Test Item	Unit	MDL	Test Result(s)				Limit
			5#	8#	9#	10#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	N.D.	500

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 4 / 22

Test Item	Unit	MDL	Test Result(s)			Limit
			11#	14#	15#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	500

Test Item	Unit	MDL	Test Result(s)			Limit
			17#	18#	19#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	500

Test Item	Unit	MDL	Test Result(s)			Limit
			21#	23#	20#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	500

Test Item	Unit	MDL	Test Result(s)			Limit
			22#	24#	25#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	N.D.	500

Test Method: With reference to EPA 3050B-1996&EPA 6010D-2018, analysis was performed by ICP-OES.

Test Item	Unit	MDL	Test Result(s)				Limit
			6#	7#	12#	13#	
Lead (Pb)	mg/kg	10	N.D.	N.D.	37	N.D.	500

Test Item	Unit	MDL	Test Result(s)	Limit
			16#	
Lead (Pb)	mg/kg	10	21	500

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 63).

2. Cadmium (Cd) Content

Test Method: With reference to EN 1122- 2001 Method B, analysis was performed by ICP-OES.

Test Item	Unit	MDL	Test Result(s)				Limit
			1#	5#	8#	9#	
Cadmium (Cd)	mg/kg	10	N.D.	N.D.	N.D.	N.D.	100

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 5 / 22

Test Item	Unit	MDL	Test Result(s)				Limit
			10#	14#	15#	17#	
Cadmium (Cd)	mg/kg	10	N.D.	N.D.	N.D.	N.D.	100

Test Item	Unit	MDL	Test Result(s)				Limit
			18#	20#	22#	24#	
Cadmium (Cd)	mg/kg	10	N.D.	N.D.	N.D.	N.D.	100

Test Item	Unit	MDL	Test Result(s)	Limit
			25#	
Cadmium (Cd)	mg/kg	10	N.D.	100

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 23).

3. AZO Content

Test Method: With reference to EN ISO 17234-1:2024 and EN ISO 17234-2:2011, analysis was performed by GC-MS.

Test Items		MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
CAS No.	prohibitive aromatic amines		1#	14#	
92-67-1	4-Aminobiphenyl	5	N.D.	N.D.	30
92-87-5	Benzidine	5	N.D.	N.D.	30
95-69-2	4-Chloro-o-toluidine	5	N.D.	N.D.	30
91-59-8	2-Naphthylamine	5	N.D.	N.D.	30
97-56-3	O-Aminoazotoluene	5	N.D.	N.D.	30
99-55-8	5-nitro-o-toluidine	5	N.D.	N.D.	30
106-47-8	4-Chloroaniline	5	N.D.	N.D.	30
615-05-4	4-methoxy-m-phenylenediamine	5	N.D.	N.D.	30
101-77-9	4,4'-methylenedianiline	5	N.D.	N.D.	30
91-94-1	3,3'-Dichlorobenzidine	5	N.D.	N.D.	30
119-90-4	3,3'-Dimethoxybenzidine	5	N.D.	N.D.	30
119-93-7	3,3'-Dimethylbenzidine	5	N.D.	N.D.	30

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 6 / 22

Test Items		MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
CAS No.	prohibitive aromatic amines		1#	14#	
838-88-0	4,4'-methylenedi-o-toluidine	5	N.D.	N.D.	30
120-71-8	P-Cresidine	5	N.D.	N.D.	30
101-14-4	4,4'-Methylene-bis-(2-Chloro-aniline)	5	N.D.	N.D.	30
101-80-4	4,4'-oxydianiline	5	N.D.	N.D.	30
139-65-1	4,4'-Thiodianiline	5	N.D.	N.D.	30
95-53-4	O-Toluidine	5	N.D.	N.D.	30
95-80-7	4-methyl-m-phenylenediamine	5	N.D.	N.D.	30
137-17-7	2,4,5-Trimethylaniline	5	N.D.	N.D.	30
60-09-03	4-Aminoazobenzene	5	N.D.	N.D.	30
90-04-0	O-Anisidine	5	N.D.	N.D.	30

Test Items		MDL (mg/kg)	Test Results (mg/kg)	Limit (mg/kg)
CAS No.	prohibitive aromatic amines		15#	
92-67-1	4-Aminobiphenyl	5	N.D.	30
92-87-5	Benzidine	5	N.D.	30
95-69-2	4-Chloro-o-toluidine	5	N.D.	30
91-59-8	2-Naphthylamine	5	N.D.	30
97-56-3	O-Aminoazotoluene	5	N.D.	30
99-55-8	5-nitro-o-toluidine	5	N.D.	30
106-47-8	4-Chloroaniline	5	N.D.	30
615-05-4	4-methoxy-m-phenylenediamine	5	N.D.	30
101-77-9	4,4'-methylenedianiline	5	N.D.	30
91-94-1	3,3'-Dichlorobenzidine	5	N.D.	30
119-90-4	3,3'-Dimethoxybenzidine	5	N.D.	30
119-93-7	3,3'-Dimethylbenzidine	5	N.D.	30
838-88-0	4,4'-methylenedi-o-toluidine	5	N.D.	30
120-71-8	P-Cresidine	5	N.D.	30
101-14-4	4,4'-Methylene-bis-(2-Chloro-aniline)	5	N.D.	30
101-80-4	4,4'-oxydianiline	5	N.D.	30

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 7 / 22

Test Items		MDL (mg/kg)	Test Results (mg/kg)	Limit (mg/kg)
CAS No.	prohibitive aromatic amines		15#	
139-65-1	4,4'-Thiodianiline	5	N.D.	30
95-53-4	O-Toluidine	5	N.D.	30
95-80-7	4-methyl-m-phenylenediamine	5	N.D.	30
137-17-7	2,4,5-Trimethylaniline	5	N.D.	30
60-09-03	4-Aminoazobenzene	5	N.D.	30
90-04-0	O-Anisidine	5	N.D.	30

Test Method: With reference to EN ISO 14362-1:2017 and EN ISO 14362-3:2017, analysis was performed by GC-MS.

Test Items		MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
CAS No.	prohibitive aromatic amines		2#	3#	
92-67-1	4-Aminobiphenyl	5	N.D.	N.D.	30
92-87-5	Benzidine	5	N.D.	N.D.	30
95-69-2	4-Chloro-o-toluidine	5	N.D.	N.D.	30
91-59-8	2-Naphthylamine	5	N.D.	N.D.	30
97-56-3	O-Aminoazotoluene	5	N.D.	N.D.	30
99-55-8	5-nitro-o-toluidine	5	N.D.	N.D.	30
106-47-8	4-Chloroaniline	5	N.D.	N.D.	30
615-05-4	4-methoxy-m-phenylenediamine	5	N.D.	N.D.	30
101-77-9	4,4'-methylenedianiline	5	N.D.	N.D.	30
91-94-1	3,3'-Dichlorobenzidine	5	N.D.	N.D.	30
119-90-4	3,3'-Dimethoxybenzidine	5	N.D.	N.D.	30
119-93-7	3,3'-Dimethylbenzidine	5	N.D.	N.D.	30
838-88-0	4,4'-methylenedi-o-toluidine	5	N.D.	N.D.	30
120-71-8	P-Cresidine	5	N.D.	N.D.	30
101-14-4	4,4'-Methylene-bis-(2-Chloro-aniline)	5	N.D.	N.D.	30
101-80-4	4,4'-oxydianiline	5	N.D.	N.D.	30
139-65-1	4,4'-Thiodianiline	5	N.D.	N.D.	30
95-53-4	O-Toluidine	5	N.D.	N.D.	30

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 8 / 22

Test Items		MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
CAS No.	prohibitive aromatic amines		2#	3#	
95-80-7	4-methyl-m-phenylenediamine	5	N.D.	N.D.	30
137-17-7	2,4,5-Trimethylaniline	5	N.D.	N.D.	30
60-09-03	4-Aminoazobenzene	5	N.D.	N.D.	30
90-04-0	O-Anisidine	5	N.D.	N.D.	30

Test Items		MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
CAS No.	prohibitive aromatic amines		4#	11#	
92-67-1	4-Aminobiphenyl	5	N.D.	N.D.	30
92-87-5	Benzidine	5	N.D.	N.D.	30
95-69-2	4-Chloro-o-toluidine	5	N.D.	N.D.	30
91-59-8	2-Naphthylamine	5	N.D.	N.D.	30
97-56-3	O-Aminoazotoluene	5	N.D.	N.D.	30
99-55-8	5-nitro-o-toluidine	5	N.D.	N.D.	30
106-47-8	4-Chloroaniline	5	N.D.	N.D.	30
615-05-4	4-methoxy-m-phenylenediamine	5	N.D.	N.D.	30
101-77-9	4,4'-methylenedianiline	5	N.D.	N.D.	30
91-94-1	3,3'-Dichlorobenzidine	5	N.D.	N.D.	30
119-90-4	3,3'-Dimethoxybenzidine	5	N.D.	N.D.	30
119-93-7	3,3'-Dimethylbenzidine	5	N.D.	N.D.	30
838-88-0	4,4'-methylenedi-o-toluidine	5	N.D.	N.D.	30
120-71-8	P-Cresidine	5	N.D.	N.D.	30
101-14-4	4,4'-Methylene-bis-(2-Chloro-aniline)	5	N.D.	N.D.	30
101-80-4	4,4'-oxydianiline	5	N.D.	N.D.	30
139-65-1	4,4'-Thiodianiline	5	N.D.	N.D.	30
95-53-4	O-Toluidine	5	N.D.	N.D.	30
95-80-7	4-methyl-m-phenylenediamine	5	N.D.	N.D.	30
137-17-7	2,4,5-Trimethylaniline	5	N.D.	N.D.	30
60-09-03	4-Aminoazobenzene	5	N.D.	N.D.	30
90-04-0	O-Anisidine	5	N.D.	N.D.	30

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 9 / 22

Test Items		MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
CAS No.	prohibitive aromatic amines		19#	21#	
92-67-1	4-Aminobiphenyl	5	N.D.	N.D.	30
92-87-5	Benzidine	5	N.D.	N.D.	30
95-69-2	4-Chloro-o-toluidine	5	N.D.	N.D.	30
91-59-8	2-Naphthylamine	5	N.D.	N.D.	30
97-56-3	O-Aminoazotoluene	5	N.D.	N.D.	30
99-55-8	5-nitro-o-toluidine	5	N.D.	N.D.	30
106-47-8	4-Chloroaniline	5	N.D.	N.D.	30
615-05-4	4-methoxy-m-phenylenediamine	5	N.D.	N.D.	30
101-77-9	4,4'-methylenedianiline	5	N.D.	N.D.	30
91-94-1	3,3'-Dichlorobenzidine	5	N.D.	N.D.	30
119-90-4	3,3'-Dimethoxybenzidine	5	N.D.	N.D.	30
119-93-7	3,3'-Dimethylbenzidine	5	N.D.	N.D.	30
838-88-0	4,4'-methylenedi-o-toluidine	5	N.D.	N.D.	30
120-71-8	P-Cresidine	5	N.D.	N.D.	30
101-14-4	4,4'-Methylene-bis-(2-Chloro-aniline)	5	N.D.	N.D.	30
101-80-4	4,4'-oxydianiline	5	N.D.	N.D.	30
139-65-1	4,4'-Thiodianiline	5	N.D.	N.D.	30
95-53-4	O-Toluidine	5	N.D.	N.D.	30
95-80-7	4-methyl-m-phenylenediamine	5	N.D.	N.D.	30
137-17-7	2,4,5-Trimethylaniline	5	N.D.	N.D.	30
60-09-03	4-Aminoazobenzene	5	N.D.	N.D.	30
90-04-0	O-Anisidine	5	N.D.	N.D.	30

Remark: The above limit value was quoted according to EC Regulation 1907/2006 REACH Annex XVII (entry 43).

***** To be continued *****

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 10 / 22

4. Color Fastness to Rubbing

Test Method: With reference to EN ISO 105-X12:2016.

Test Items		Unit	Test Result(s)			Client's Required Limit
			1#	2#	3#	
Color Fastness to Rubbing	Dry	grade	4-5	4-5	4-5	≥2-3
	Wet	grade	4-5	4-5	4-5	≥2-3

Test Items		Unit	Test Result(s)			Client's Required Limit
			4#	11#	14#	
Color Fastness to Rubbing	Dry	grade	4-5	4-5	4-5	≥2-3
	Wet	grade	4-5	4-5	4-5	≥2-3

Test Items		Unit	Test Result(s)			Client's Required Limit
			15#	19#	21#	
Color Fastness to Rubbing	Dry	grade	4-5	4-5	4-5	≥2-3
	Wet	grade	4-5	4-5	4-5	≥2-3

5. PAHs content

Test Method: With reference to AfPS GS 2019:01 PAK, analysis was performed by GC-MS.

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			1#	5#	
Benzo[a]pyrene	50-32-8	0.1	N.D.	N.D.	1
Benzo[e]pyrene	192-97-2	0.1	N.D.	N.D.	1
Benzo[a]anthracene	56-55-3	0.1	N.D.	N.D.	1
Chrysene	218-01-9	0.1	N.D.	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	N.D.	1
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	N.D.	1

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 11 / 22

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			8#	9#	
Benzo[a]pyrene	50-32-8	0.1	N.D.	N.D.	1
Benzo[e]pyrene	192-97-2	0.1	N.D.	N.D.	1
Benzo[a]anthracene	56-55-3	0.1	N.D.	N.D.	1
Chrysene	218-01-9	0.1	N.D.	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	N.D.	1
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	N.D.	1

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			10#	14#	
Benzo[a]pyrene	50-32-8	0.1	N.D.	N.D.	1
Benzo[e]pyrene	192-97-2	0.1	N.D.	N.D.	1
Benzo[a]anthracene	56-55-3	0.1	N.D.	N.D.	1
Chrysene	218-01-9	0.1	N.D.	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	N.D.	1
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	N.D.	1

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			15#	17#	
Benzo[a]pyrene	50-32-8	0.1	N.D.	N.D.	1
Benzo[e]pyrene	192-97-2	0.1	N.D.	N.D.	1
Benzo[a]anthracene	56-55-3	0.1	N.D.	N.D.	1
Chrysene	218-01-9	0.1	N.D.	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	N.D.	1

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 12 / 22

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			15#	17#	
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	N.D.	1

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			18#	20#	
Benzo[a]pyrene	50-32-8	0.1	N.D.	N.D.	1
Benzo[e]pyrene	192-97-2	0.1	N.D.	N.D.	1
Benzo[a]anthracene	56-55-3	0.1	N.D.	N.D.	1
Chrysene	218-01-9	0.1	N.D.	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	N.D.	1
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	N.D.	1

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			22#	24#	
Benzo[a]pyrene	50-32-8	0.1	N.D.	N.D.	1
Benzo[e]pyrene	192-97-2	0.1	N.D.	N.D.	1
Benzo[a]anthracene	56-55-3	0.1	N.D.	N.D.	1
Chrysene	218-01-9	0.1	N.D.	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	N.D.	1
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	N.D.	1

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)		Limit (mg/kg)
			25#		
Benzo[a]pyrene	50-32-8	0.1	N.D.		1
Benzo[e]pyrene	192-97-2	0.1	N.D.		1
Benzo[a]anthracene	56-55-3	0.1	N.D.		1

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 13 / 22

Test Items	CAS No.	MDL (mg/kg)	Test Results (mg/kg)	Limit (mg/kg)
			25#	
Chrysene	218-01-9	0.1	N.D.	1
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	1
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	1
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	1
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	1

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 72).

6. Phthalates Content

Test Method: With reference to EN 14372-2004, analysis was performed by GC-MS.

Test Items	Unit	MDL	Test Results		Limit
			1#	5#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			1#	5#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			8#	9#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 14 / 22

Test Items	Unit	MDL	Test Results		Limit
			8#	9#	
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			8#	9#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			10#	14#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			10#	14#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			15#	17#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 15 / 22

Test Items	Unit	MDL	Test Results		Limit
			15#	17#	
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			15#	17#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			18#	20#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			18#	20#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			22#	24#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	N.D.	---

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 16 / 22

Test Items	Unit	MDL	Test Results		Limit
			22#	24#	
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results		Limit
			22#	24#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.015	≤0.1

Test Items	Unit	MDL	Test Results	Limit
			25#	
Dibutyl Phthalate (DBP)	%	0.005	N.D.	---
Benzylbutyl Phthalate (BBP)		0.005	N.D.	---
Di-(2-ethylhexyl)Phthalate (DEHP)		0.005	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	≤0.1

Test Items	Unit	MDL	Test Results	Limit
			25#	
Di-iso-nonylphthalate (DINP)	%	0.005	N.D.	---
Di-n-octylphthalate (DNOP)		0.005	N.D.	---
Di-iso-decylphthalate (DIDP)		0.005	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	≤0.1

Remark: The above limit value was quoted according to EC Regulation 1907/2006, REACH Annex XVII (entry 51&52).

Note: 1. MDL= Method Detection Limit
2. N.D. = Not Detected, <MDL

***** To be continued *****

Suzhou Yacoo Wonder Testing Technology Co.,Ltd.

Add.: 8/F, No.112, Xinqing Road, Industrial Park, Suzhou, Jiangsu, China.

Tel: +86 512 6760 0956

Customer Service: service@wondertesting.cn

Web.: www.yacoo-wondertesting.com

Report Query: report@wondertesting.cn


TEST REPORT

Report No.: YW202609011801E


Date: Oct. 22, 2026

Page: 17 / 22

SAMPLE PHOTO(S)



1#



1#




2#



3#



4#




5#

TEST REPORT


Report No.: YW202609011801E

Date: Oct. 22, 2026


Page: 18 / 22




6#



7#




8#



9#



10#



11#

TEST REPORT


Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 19 / 22




12#



13#




14#



14#



15#



15#

TEST REPORT


Report No.: YW202609011801E

Date: Oct. 22, 2026


Page: 20 / 22




16#




17#




17#



18#



19#




20#

TEST REPORT


Report No.: YW202609011801E

Date: Oct. 22, 2026


Page: 21 / 22




21#




22#



23#



24#



25#

TEST REPORT

Report No.: YW202609011801E

Date: Oct. 22, 2026

Page: 22 / 22

Statement:

1. This report is considered invalid without approved signature and special seal of the laboratory.
2. The sample(s) and sample(s) information was/were provided by the applicant who should be responsible for the authenticity.
3. The result(s) shown in this report refer(s) only to the sample(s) tested.
4. Without written approval of the laboratory, this report shall not be reproduced except in full. The report is invalid if altered.
5. Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule ($w=0$) stated in LAC-G8.09/2019. According to this rule, the judgement of conformity is based on the comparing test results with limits. The statement of conformity is based on the test results, but does not include the measurement uncertainty.
6. Without prior approval of YACOO WONDER, the client shall not use the testing data and results for improper publicity.
7. If there is any objection to the report, client shall lodge a complaint with the company on the 15 working days from the date of receipt of the report. No late application will be accepted.

***** END OF REPORT *****